



Roof Tile Effect Insulated Panel KS1000 RT Data Sheet



KS1000 RT

Roof Tile


Applications

KS1000 RT looks like a traditional tiled roof but it is a modern Kingspan insulated panel with a shaped exterior that performs better than any tiling system. The insulation is built-in and can be used for any domestic or commercial building with a roof pitch of 12° or more after deflection. The traditional look hides a sophisticated system that is easy to construct and complies with all contemporary building standards.

Available Lengths

Standard Lengths	2.1 – 11.5m
Longer Lengths (non-standard)	11.5- 15.7m
Shorter Lengths (non-standard)	Below 2.1m

Note: Panel lengths are based on tile module of 325mm plus 150mm for cutbacks of 160mm or 100mm for 100mm cutbacks. Additional costs and transport restrictions may apply for non-standard lengths. All lengths may change for export (outside of the UK)



Dimensions, Weight & Thermal Performance

Core Thickness (mm)	45	60	80	100
Overall Thickness (mm)	85	100	120	140
U-value (W/m²K)*	0.45	0.33	0.25	0.20
Weight kg/m² 0.5 Steel/0.4 Steel	10.7	11.3	12.2	13.1

The KS1000 RT insulated roof panels have a Thermal Transmittance (U value), calculated using the method required by the Building Regulations Part L2 (England & Wales) and Building Standards Section 6 (Scotland).

KS1000 RT

Roof Tile

Insulation Core

KS1000 RT insulated roof panels are manufactured with an ECOsafe and FIREsafe polyisocyanurate (PIR) core.

Fire

The external and internal faces of the panel to be Class 0 in accordance with the Building Regulations when tested to BS 476: Part 6: 2009 and Part 7: 1997. The panel is rated SAA when tested to BS 476: Part 3: 2004.

This FIREsafe system has passed all the requirements of LPS1181: 2005: Part 1: Issue 1.2, ceiling lining tests by the Loss Prevention Certification Board (LPCB) certified to LPS 1181 Grade EXT-B. Reaction to fire classification according to BS EN 13501-1:2007+A1:2009: B-s2,d0.



LPS 1181 : Issue 1.2
Cert No: 260a & 186a

Environmental

Kingspan Insulated Panels produced in the UK are certified to BES 6001 (Framework Standard for the Responsible Sourcing of Construction Products) 'Very Good'. Kingspan Insulated Panels directly contribute to BREEAM/LEED credits.

Air Leakage

An air leakage rate of 3m³/hr/m² at 50Pa or less can be achieved when using Kingspan insulated roof and wall panels.

Acoustic

Sound Reduction Index (SRI)

Hz*	63	125	250	500	1K	2K	4K	8K
SRI (dB)	20	19	21	22	22	32	38	44

* Frequency

The KS1000 RT insulated roof panel has a single figure weighted sound reduction $R_w = 25\text{dB}$.

Biological

Kingspan panels are normally immune to attack from mould, fungi, mildew and vermin. No urea formaldehyde is used in the construction, and the panels are not considered deleterious

Materials

Substrate

- Kingspan XL Forté, Kingspan AQUAsafe, Kingspan AQUAsafe55 and Kingspan CLEANsafe: Metallic protected steel to BS EN 10346:2015.thickness 0.5mm. CLEANsafe 15: Metallic protected steel to BS EN10346:2015.thickness 0.4mm.
- Polyurthane & CLEANsafe 15: Hot dip zinc coated to BS En 10346: 2009, Standard internal steel thickness 0.4mm, Stucco embossed.

Coatings - External Weather Sheet

- Kingspan XL Forté: consists of a multi-layer organic coating, embossed with a traditional leather-grain finish.
- Polyurethane Coating: High performance polymer coating applied to the weather side of the panel. Designed to achieve excellent endurance characteristics.

Coatings - Internal Liner Sheet

- Kingspan CLEANsafe 15: The coating has been developed for use as the internal lining of insulated panels. Standard colour is "bright white" with an easily cleaned surface.
- Kingspan AQUAsafe: The coating has been developed for use as the internal lining of insulated panels to suit high humidity internal environments.
- Kingspan AQUAsafe 55: The coating has been developed for use as the internal lining of insulated panels to swimming pool internal environments.
- Kingspan CLEANsafe 120: The coating has been developed for use as the internal lining of insulated panels where a high level of cleanliness and hygiene is required, and the panels are to be cleaned down on a regular basis.

KS1000 RT

Roof Tile

Panel End Cut Back

Standard Cut Back	160mm
Cut Back for up to 6.275m lengths	100mm

Note: We do not recommend end lapping KS1000RT panels

Product Tolerance

Cut to Length	-5mm +5mm
Cover Width	-0mm +3mm
Thickness	-2mm +2mm
End Square	-3mm +3mm

Handling

The KS1000 RT insulated roof panel can be manufactured in left to right handed (LH) only.

Quality & Durability

KS1000 RT insulated roof panels are manufactured from the highest quality materials, using state of the art production equipment to rigorous quality control standards, complying with BS EN ISO 9001 Standard, ensuring long term reliability and service life. The panels are also being manufactured under Environmental Management System Certification BS EN ISO 14001. Compliant to BS OHSAS 18001 Occupational Health and Safety.



Warranty

Kingspan Panel Warranty covering the following subject to project specific information:

- 25 year thermal performance warranty;
- 25 year structural performance warranty;
- Up to 40 year external coating warranty.

Packing

KS1000 RT insulated roof panels are stacked weather sheet to weather sheet (to minimise pack height). The top, bottom, sides and ends are protected with foam and timber packing and the entire pack is wrapped in plastic.

Core Thickness (mm)	45	60	80	100
No. of panels in Pack	10	8	8	6

Note: Applies to UK pack sizes. Please contact Kingspan Technical Services for export information. Quantities are reduced for exceptionally long panels.

Sea Freight

Fully timber crated packs are available on projects requiring delivery by sea freight shipping, at additional costs. Alternatively, steel containers can be used. Special loading charges apply.

Delivery

All deliveries (unless indicated otherwise) are by road transport to project site. Off-loading is the responsibility of the client.

Site Installation Procedure

Site assembly instructions are available from Kingspan envirocare Technical Services.

KS1000 RT

Roof Tile

Structural Tables

Unfactored load/span table (use unfactored calculated design wind load values)

External Sheet 0.5mm (Steel), Inner Sheet 0.4mm (Steel)

Single Span Condition

Core Thickness (mm)	Load Type	Uniformly distributed imposed load, kN/m ²										
		Span L in metres										
		1.0	1.2	1.4	1.6	1.8	2.0	2.2	2.4	2.6	2.8	3.0
45	Downwards	4.33	2.92	1.98	1.37	0.96	0.69	-	-	-	-	-
	Suction	4.47	3.12	2.31	1.78	1.42	1.16	-	-	-	-	-
60	Downwards	5.34	3.68	2.68	2.00	1.45	1.06	0.79	0.58	-	-	-
	Suction	5.49	3.83	2.83	2.18	1.74	1.42	1.19	1.01	-	-	-
80	Downwards	6.68	4.61	2.36	2.55	1.99	1.59	1.30	1.01	0.77	0.60	-
	Suction	6.86	4.79	3.54	2.73	2.17	1.77	1.48	1.25	1.08	0.94	-
100	Downwards	8.03	5.54	4.04	3.07	2.40	1.92	1.57	1.30	1.09	0.93	0.79
	Suction	8.22	5.74	4.24	3.26	2.60	2.12	1.77	1.50	1.29	1.12	0.99

Double Span Condition

Core Thickness (mm)	Load Type	Uniformly distributed imposed load, kN/m ²										
		Span L in metres										
		1.0	1.2	1.4	1.6	1.8	2.0	2.2	2.4	2.6	2.8	3.0
45	Downwards	4.33	2.98	2.17	1.64	1.28	1.02	0.83	0.68	0.57	-	-
	Suction	4.47	3.12	2.31	1.78	1.42	1.16	0.97	0.83	0.71	-	-
60	Downwards	5.34	3.68	2.68	2.03	1.59	1.27	1.03	0.85	0.72	-	-
	Suction	5.49	3.83	2.83	2.18	1.74	1.42	1.19	1.01	0.87	-	-
80	Downwards	6.68	4.61	3.36	2.55	1.99	1.59	1.30	1.07	0.90	0.76	0.65
	Suction	6.86	4.79	3.54	2.73	2.17	1.77	1.48	1.25	1.08	0.94	0.83
100	Downwards	8.03	5.54	4.04	3.07	2.40	1.92	1.57	1.30	1.09	0.93	0.79
	Suction	8.22	5.74	4.24	3.26	2.60	2.12	1.77	1.50	1.29	1.12	0.99

Notes:

1. Values have been calculated using the method described in BS EN 14509 2013, for dark coloured panels.
2. Deflection limit for: downward loading is L/200 and suction loading is L/150.
3. The actual wind suction load resisted by the panel is dependent upon the number of fasteners used and the purlin thickness as well as fastener material.
4. The fastener calculation should be carried out in accordance with the appropriate standards. For further advice please contact Kingspan envirocare Technical Services.
5. The allowable steelwork tolerance between bearing planes of adjacent supports is +/- 5mm
6. Load span tables for the panel specifications not shown are available from Kingspan envirocare Technical Services.

UK

Kingspan Limited
Greenfield Business Park No. 2,
Greenfield, Holywell, Flintshire,
North Wales, CH8 7GJ
T: +44 (0) 1352 716100
F: +44 (0) 1352 710161
www.kingspanpanels.co.uk

For the product offering in other markets
Please contact your local sales representative
or visit www.kingspanpanels.com

Care has been taken to ensure that the contents of this publication are accurate, but Kingspan Limited and its subsidiary companies do not accept responsibility for errors or for information that is found to be misleading. Suggestions for, or description of, the end use of application of products or methods of working are for information only and Kingspan Limited and its subsidiaries accept no liability in respect thereof.

xx/2018