

2020
FLEXITEC
Multi-surface GRP roofing system

Application Overview

Substrate (Surface to be Coated)	Felt	Asphalt	Single Ply*	GRP / Liquid Roofing System*	Metal	OSB3 TG4	Concrete / Screed	Tissue Faced Insulation
Primer	Flexitec 2020 Primer	Flexitec 2020 Primer	Flexitec 2020 Primer*	No Primer Usually Required*	Metallic Primer	Stripe Coat T&G Joints with Flexitec 2020 Primer	Flexitec 2020 Primer	Flexitec 2020 Primer
Reinforcement	225g/m ² CSM	225g/m ² CSM	225g/m ² CSM	225g/m ² CSM	225g/m ² CSM	225g/m ² CSM	225g/m ² CSM	225g/m ² CSM
First Coat Coverage Rate	0.85 - 1.15 l/m ² (1.2 - 1.6 kg/m ²)	0.85 - 1.15 l/m ² (1.2 - 1.6 kg/m ²)	0.85 l/m ² (1.2 kg/m ²)	1.0 - 1.15 l/m ² (1.4 - 1.6 kg/m ²)	1.0 - 1.15 l/m ² (1.4 - 1.6 kg/m ²)			
Second Coat Coverage Rate	0.5 l/m ² (0.7 kg/m ²)	0.5 l/m ² (0.7 kg/m ²)	0.5 l/m ² (0.7 kg/m ²)	0.5 l/m ² (0.7 kg/m ²)	0.5 l/m ² (0.7 kg/m ²)	0.5 l/m ² (0.7 kg/m ²)	0.5 l/m ² (0.7 kg/m ²)	Light Grey Only 0.5 l/m ² (0.7 kg/m ²)

* Adhesion tests may be required for certain substrates to confirm preparation and priming requirements.

All coverage rates are indicative only and subject to confirmation on site.